



材質表 Grades

Grade	WC grain size	Co	Hardness		TRS	K _{IC}	4πσ	HC
			HV [ISO 3878]	HRC [ISO 3738]				
	[μm]	[%]			[N/mm ²] [ISO 3327]	[Mnm ^{-3/2}]	[μTm ³ /kg]	[kA/m]
KFM 38/308	0.3	8.0	1970	94.0	4300	9.2	12.0	35.0
KFM 47	0.4	7.0	1980	94.0	4500	9.0	11.0	36.0
KFM 39	0.3	9.0	1950	93.9	4500	9.3	14.5	36.0
KFM 66/606	0.6	6.0	1900	93.8	4000	9.3	9.3	28.0
KFM 44	0.5	12.0	1680	92.5	4000	10.0	18.7	26.3
KFM 40	0.6	10.0	1610	92.0	3800	10.5	16.0	20.1
KFM G20	3.0	11.5	1300	n.m	2600	n.m	19.3	14.0